

12

**EUROPEAN PATENT APPLICATION**

published in accordance with Art. 158(3) EPC

21 Application number: **87905473.2**

51 Int. Cl.: **C 08 G 69/26, C 08 G 69/32,**  
**C 08 G 69/40, C 08 G 69/42**

22 Date of filing: **19.08.87**

Data of the international appli-  
cation taken as a basis:

86 International application number:  
**PCT/JP 87/00617**

87 International publication number:  
**WO 88/01283 (25.02.88 88/5)**

30 Priority: **20.08.86 JP 192838/86**

71 Applicant: **mitsui petrochemical industries,**  
**LTD., 2-5, Kasumigasaki 3-chome Chiyoda-ku,**  
**Tokyo 100 (JP)**

43 Date of publication of application: **07.09.88**  
**Bulletin 88/36**

72 Inventor: **SAKASHITA, Takeshi, 1-40, Aoki-cho 3-chome**  
**Iwakuni-shi, Yamaguchi 740 (JP)**  
Inventor: **SHIMODA, Tomoaki, 4-9, Waki 2-chome**  
**Waki-cho Kuga-gun, Yamaguchi 740 (JP)**

84 Designated Contracting States: **DE FR GB IT**

74 Representative: **Myerscough, Philip Boyd et al,**  
**J.A.Kemp & Co. 14, South Square Gray's Inn, London,**  
**WC1R 5EU (GB)**

54 **AROMATIC POLYAMIDES AND AGENTS FOR IMPARTING GAS BARRIER PROPERTIES TO THEM.**

57 Aromatic polyamides excellent in melt moldability and having good heat resistance, mechanical strength, transparency and excellent gas barrier properties. The aromatic polyamides can be used as the material for containers because of their excellent gas barrier properties, and can protect a product contained therein from a gas.

**EP 0 280 736 A1**

- 1 -

## SPECIFICATION

AROMATIC POLYAMIDE AND GAS-BARRIER PROPERTY  
IMPARTING AGENT COMPOSED OF IT

## TECHNOLOGICAL FIELD

5           This invention relates to an aromatic poly-  
amide, and a gas-barrier property imparting agent based  
on the excellent gas barrier property of the aromatic  
polyamide. More specifically, this invention relates to  
10 an aromatic polyamide having excellent melt-moldability,  
thermal stability, mechanical strength, transparency and  
gas-barrier property which are the properties suitable  
for use as a material for containers, and to a gas-  
barrier property imparting agent composed of the poly-  
amide.

## 15           BACKGROUND TECHNOLOGY

Glass has widely been used heretofore as a  
material for containers holding seasonings, oils, beer,  
wines and liquors such as sake, cooling drinks such as  
carbonated drinks, cosmetics, and detergents. Glass  
20 containers have excellent gas-barrier property, but since  
the cost of their production is high, empty bottles after  
use are recovered and recycled for further use. The  
glass containers have the defect that they are heavy and  
require large transportation expenses, and are also  
25 fragile and inconvenient to handle.

To eliminate the aforesaid defects of the glass  
containers, various plastic containers have increasingly  
replaced the glass containers. Various plastics have  
been employed as materials for the plastic containers  
30 depending upon the type and the purpose of use of an  
article to be held. Among these plastic materials,  
polyethylene terephthalate has especially superior gas-  
barrier property and transparency, and has therefore been  
used as a material for containers which hold seasonings,  
35 cooling drinks, detergents and cosmetics. For containers  
holding beer and carbonated drinks which require most

- 2 -

rigorous gas-barrier property among them, polyethylene terephthalate has not yet proved to be entirely satisfactory. When polyethylene terephthalate is to be used in the containers, their gas-barrier property should be increased by increasing the wall thickness of the containers.

Aliphatic polyamides such as nylon 6 and nylon 66 show better gas-barrier property than polyethylene terephthalate in the dry state, but since these polymers generally have a water absorption of about 10 % and in the water-absorbed state, they have lower gas-barrier property than polyethylene terephthalate. Crystalline polyamides containing a cyclic hydrocarbon group are disclosed in Japanese Laid-Open Patent Publication No. 195126/1985 in an attempt to remedy this water absorba-

10 bility defect of the crystalline polyamides. These polyamides, however, have the defect of being inferior in transparency because they are crystalline.

It is an object of this invention to provide a novel aromatic polyamide.

Another object of this invention is to provide a novel aromatic polyamide which has excellent gas-barrier property with respect to gases such as oxygen and carbon dioxide gas and excellent transparency and are superior in chemical and physical properties such as thermal properties, mechanical properties, chemical resistance and water resistance.

Still another object of this invention is to provide a gas-barrier property imparting agent composed of the aforesaid aromatic polyamide by utilizing the excellent gas-barrier property of the aromatic polyamide.


#### DISCLOSURE OF THE INVENTION

According to this invention, the above objects of this invention along with its advantages are achieved by an aromatic polyamide characterized in that


(1) it is composed of a random arrangement of

- 3 -

isophthaloyldiamine component recurring units represented by the following formula (I)



wherein  $\text{R}^{\circ}$  is a divalent hydrocarbon group having 4 to 25 carbon atoms, and diacyloyldiamine component recurring units represented by the following formula (II)



wherein  $\text{R}^{\circ}$  is as defined above, and Ar is a divalent aromatic hydrocarbon group containing 6 to 20 carbon atoms other than the 1,3-phenylene group,

(2) it has such a composition that based on the entire recurring units, the proportion of the isophthaloyldiamine component units is 50 to 100 mole % and the proportion of the diacyloyldiamine component units is 50 to 0 mole %,

(3) it has a melt flow rate (MFR), measured at 300 °C under a load of 2 kg, of 0.01 to 100 g/10 min.,

(4) it has a crystallinity, measured by X-ray diffractometry, of not more than 7 %, and

(5) it has a glass transition temperature ( $T_g$ ) of 110 to 240 °C.

The recurring units constituting the aromatic polyamide of this invention are the isophthaloyldiamine component units of formula (I) and the diacyloyldiamine component units of formula (II).

In formula (I),  $\text{R}^{\circ}$  is a divalent hydrocarbon group having 4 to 25 carbon atoms, such as divalent aliphatic hydrocarbon groups having 4 to 25 carbon atoms, divalent alicyclic hydrocarbon groups having 6 to 25 carbon atoms and containing at least one alicyclic hydrocarbon ring, and divalent aromatic hydrocarbon groups having 6 to 25 carbon atoms and containing at least one

aromatic hydrocarbon ring.

Preferred as  $R^O$  are mixtures of divalent aliphatic hydrocarbon groups having 4 to 25 carbon atoms and divalent alicyclic hydrocarbon groups having 6 to 25 carbon atoms and containing at least one alicyclic hydrocarbon ring, and mixtures of divalent aliphatic hydrocarbon groups having 4 to 25 carbon atoms and divalent aromatic hydrocarbon groups having 6 to 25 carbon atoms and containing at least one aromatic hydrocarbon ring.

Above all, a mixture of 5 to 98 mole %, especially 40 to 85 mole %, of such a divalent aliphatic hydrocarbon group and 95 to 2 mole %, especially 60 to 15 mole %, or a mixture of 5 to 98 mole %, especially 40 to 85 mole %, of the divalent aliphatic hydrocarbon group and 95 to 2 moles, especially 60 to 15 mole %, of such a divalent aromatic hydrocarbon groups is preferred.

The divalent hydrocarbon residue  $R^O$  in formula (I) is derived from a diamine of the formula  $NH_2-R^O-NH_2$ .

Diamines in which  $R^O$  is a divalent aliphatic hydrocarbon group having 4 to 25 carbon atoms may be, for example, 1,4-diaminobutane, 1,5-diaminopentane, 1,6-diaminohexane, 1,7-diaminoheptane, 1,8-diaminooctane, 1,9-diaminononane, 1,10-diaminodecane, 1,11-diaminoundecane, 1,12-diaminododecane, 1,13-diaminotridecane, 1,14-diaminotetradecane, 1,15-diaminopentadecane, 1,16-diaminohexadecane, 1,17-diaminoheptadecane, 1,18-diaminooctadecane, 1,19-diaminononadecane and 1,20-diaminoeicosane. These alkylenediamines may be used singly or in combination. Among these alkylene diamines, those having 6 to 16 carbon atoms are preferred, and 1,6-diaminohexane is especially preferred.

Examples of diamines in which  $R^O$  is a divalent alicyclic hydrocarbon group containing at least one alicyclic hydrocarbon ring and having 6 to 25 carbon atoms include 1,3-diaminocyclohexane, 1,4-diaminocyclohexane, 1,3-bis(aminomethyl)cyclohexane, 1,4-bis(amino-

- 5 -

methyl)cyclohexane, isophoronediamine, piperazine,  
 2,5-dimethylpiperazine, bis(4-aminocyclohexyl)methane,  
 bis(4-aminocyclohexyl)propane, 4,4'-diamino-3,3'-  
 dimethyldicyclohexylmethane, 4,4'-diamino-3,3'-dimethyl-  
 5 dicyclohexylpropane, 4,4'-diamino-3,3',5,5'-tetramethyl-  
 dicyclohexylmethane, 4,4'-diamino-3,3',5,5'-tetramethyl-  
 dicyclohexylpropane, 4,4'-diamino-3,3'-dimethyldicyclo-  
 hexane, 4,4'-diamino-3,3',5,5'-tetramethyldicyclohexane,  
 alpha,alpha'-bis(4-aminocyclohexyl)-p-diisopropyl-  
 10 benzene, alpha,alpha'-bis(4-aminocyclohexyl)-m-diiso-  
 propylbenzene, alpha,alpha'-bis(4-aminocyclohexyl-1,4-  
 cyclohexane, and alpha,alpha'-bis(4-aminocyclohexyl)-  
 1,3-cyclohexane.

Examples of diamines in which  $R^O$  represents a  
 15 divalent aromatic hydrocarbon group having 6 to 25 carbon  
 atoms and containing at least one aromatic hydrocarbon  
 ring include p-phenylenediamine, m-phenylenediamine,  
 p-xylylenediamine, m-xylylenediamine, 4,4'-diaminodi-  
 phenylmethane, 4,4'-diaminodiphenylether, 4,4'-diaminodi-  
 20 phenylpropane, 4,4'-diaminodiphenylsulfone, 4,4'-diamino-  
 diphenyl sulfide, alpha,alpha'-bis(4-aminophenyl)-p-iso-  
 propylbenzene and alpha,alpha'-bis(4-aminophenyl)-m-iso-  
 propylbenzene. Among these diamines, the alicyclic  
 diamines and aromatic diamines are preferred. Of the  
 25 alicyclic diamines, bis(4-aminocyclohexyl)methane, 4,4'-  
 diamino-3,3'-dimethyldicyclohexylmethane and 1,3-bis-  
 (aminomethyl)cyclohexane are especially preferred, and  
 m-xylylenediamine, p-xylylenediamine and 4,4'-diaminodi-  
 phenylmethane are especially preferred among the aromatic  
 30 diamines.

In formula (II),  $R^O$  is as defined with regard  
 to formula (I), and Ar is a divalent aromatic hydrocarbon  
 group having 6 to 20 carbon atoms other than the 1,3-  
 phenylene group.

35 The divalent aromatic hydrocarbon group Ar in  
 formula (II) is derived from an aromatic dicarboxylic

acid represented by the formula  $\text{HOCO-Ar-COOH}$  or its functional derivative.

Examples of the aromatic dicarboxylic acid are terephthalic acid, phthalic acid, 2,6-naphthalenedi-  
5 carboxylic acid, 2,5-naphthalenedicarboxylic acid, 1,4-naphthalenedicarboxylic acid and 1,5-naphthalenedicarboxylic acid.

The recurring units of the aromatic polyamide of this invention consists of the isophthaloyldiamine  
10 component units of formula (I), or both the isophthaloyldiamine component units of formula (I) and the diacyloyldiamine component units of formula (II). In either case, where the polyamide contains a plurality of dissimilar recurring units, they are distributed or arranged at  
15 random in the polymer chain.

The aromatic polyamide of this invention can be produced, for example, by polycondensing a halide of a corresponding aromatic dicarboxylic acid (isophthalic acid or both isophthalic acid and an aromatic dicarboxylic  
20 acid of the formula  $\text{HOOC-Ar-COOH}$ ) and a diamine of the formula  $\text{NH}_2\text{-R}^{\text{O}}\text{-NH}_2$  by the solution method or the interfacial method.

It may also be produced by polycondensing a nylon salt of a corresponding aromatic dicarboxylic  
25 acid and a corresponding diamine or a prepolymer, such as an oligomer, between them by using a kneading means under shearing conditions in the heat-melted state. Among these, the third method is suitable as an industrial method. By any of these methods, a polyamide composed of  
30 50 to 100 mole % of the isophthaloyldiamine component units and 0 to 50 mole % of the diacyloyldiamine component units can be produced by adjusting the composition of the starting aromatic dicarboxylic acid component and the composition of the starting diamine component.

35 The molecular chain of the aromatic polyamide of this invention may be formed in a linear, branched or

crosslinked structure. The branched or crosslinked structure may be formed by using a trifunctional or higher polycarboxylic acid or polyamine in the above polycondensation step. Desirably, the aromatic polyamide  
5 of this invention is linear or branched, and more desirably, is of such a structure that dissolves in concentrated sulfuric acid at 30 °C.

The molecular terminal of the aromatic polyamide component may be a diamine component, an isophthalic acid component or an aromatic dicarboxylic acid component other than the isophthalic acid component. Where the molecular terminal is the alkylenediamine component, the terminal amino group may be acylated with a lower carboxylic acid or may form a salt with an acid.  
15 Where the molecular terminal is a terephthalic acid component, an isophthalic acid component or a carboxyphthalic acid component, the terminal carboxyl group may be esterified with a lower alcohol, or may be amidated with an amine, or may form a salt with an acid, or may  
20 form an acid anhydride with another carboxylic acid.

The aromatic polyamide of this invention is composed of 50 to 100 mole % of the isophthaloyldiamine component units and 50 to 0 mole % of the diacyloyldiamine component units, based on the entire recurring  
25 units. The proportion of the isophthaloyldiamine component units is preferably 60 to 90 mole %, more preferably 65 to 80 mole %, and the proportion of the diacyloyldiamine component units is preferably 40 to 10 mole %, more preferably 35 to 20 mole %.

30 The aromatic polyamide of this invention has a melt flow rate (MFR), measured at 300 °C under a load of 2 kg, of 0.01 to 100 g/10 min., preferably 0.1 to 50 g/10 min., more preferably 0.5 to 30 g/10 min.

The aromatic polyamide of this invention has a  
35 crystallinity, measured by X-ray diffractometry, of not more than 7 %, preferably not more than 5 %, more prefer-



Dably not more than 3 %.

Furthermore, the aromatic polyamide of this invention has a glass transition temperature ( $T_g$ , °C) of 110 to 240 °C, preferably 120 to 220 °C, more  
5 preferably 130 to 200 °C. The glass transition temperature is measured by a differential scanning calorimeter at a temperature elevation rate of 10 °C/min.

The intrinsic viscosity  $[\eta]$ , measured in concentrated sulfuric acid at 30 °C, of the aromatic polyamide  
10 of this invention is preferably 0.4 to 2.0 dl/g, more preferably 0.5 to 1.3 dl/g. Its crystalline melting point ( $T_m$ , °C) measured under the same measuring conditions as in the measurement of the glass transition temperature is preferably 220 to 350 °C, more preferably  
15 240 to 320 °C.

The aromatic polyamide of this invention shows excellent gas-barrier property with respect to gases such as oxygen and carbon dioxide. Accordingly, the present invention likewise provides a gas-barrier property imparting agent composed of the aromatic polyamide of this  
20 invention by utilizing the excellent gas-barrier property of the aromatic polyamide.

The aromatic polyamide of this invention as the gas-barrier property imparting agent of this invention is  
25 used as a packaging material in the form of a blend with another resin, for example polyethylene terephthalate, polycarbonate or an olefin, or in the form of a laminated structure with the other resin.

In the case of using the polyamide of this  
30 invention as a blend, the proportion of the polyamide is usually in the range of 3 to 200 parts by weight, preferably 5 to 180 parts by weight, especially preferably 5 to 150 parts by weight, per 100 parts by weight of the other resin.

35 The laminated structure is produced by, for example, multilayer simultaneous extrusion and may be in



any desired layer construction, for example, A/B or B/A/B in which A represents the polyamide of this invention and B represents the other resin. The suitable thickness of the polyamide is at least 2 microns, preferably at least 3 microns, especially at least 5 microns.

The following examples will now illustrate the present invention specifically.

The abbreviations used in the following table show the following compounds.

10	TA: terephthalic acid
	IA: isophthalic acid
	C <sub>6</sub> DA: 1,6-diaminohexane
	ACM: bis(4-aminocyclohexyl)methane
	DMACM: 4,4"-diamino-3,3"-dimethylcyclohexyl-
15	methane
	AMC: 1,3-bis(aminomethyl)cyclohexane
	MXD: m-xylylenediamine

The composition, melting point, intrinsic viscosity  $[\eta]$ , MFR and a crystallinity of the polyamide were determined by the following methods.

(1) Composition of the polyamide  
Calculated in accordance with <sup>13</sup>C-NMR in hexafluoroisopropanol solvent and elemental analysis values of the polyamide and a polyamide prepolymer as a material for the polyamide.

(2) Glass transition temperature  
Determined by performing differential thermal analysis of the resin at a temperature elevating speed of 10°C per minute by using a differential scanning calorimeter (Model DSC-2 made by Perkin Elmer Company).

(3) Intrinsic viscosity  $[\eta]$   
The relative viscosities of three 96% by weight concentrated sulfuric acid solutions of the resin in a resin concentration of 0.500 g/dl, 0.770 g/dl, and 1.00 g/dl are measured by an Ubbelohde's viscometer, and their specific viscosities are calculated. From these points

- 10 -

of the specific viscosities,  $[\eta]$  is determined by construction. The above solution was prepared at 30 °C.

(4) MFR

Measured at 300 °C under a load of 2 kg in accordance with the method of JIS K-7210.

(5) Crystallinity

Determined by broad angle (2 $\theta$ : 70° - 3°) X-ray diffraction of a press sheet sample using Rotaflex RL1-200A made by Rigaku Denki K. K.

The gas-barrier property in the Examples and Comparative Examples was evaluated by oxygen gas permeability coefficient and carbon dioxide permeability coefficient measured respectively at 25 °C by using an OXTRAN device made by Mocon Company and a PERMETRAN C-IV device made by Mocon Company.

Example 1

Terephthalic acid (89.22 g; 0.537 M), 208.17 g (1.253 M) of isophthalic acid, 193.54 g (0.92 M) of bis(4-aminocyclohexyl)methane and 106.91 g (0.92 M) of 1,6-diaminohexane were charged into a 1-liter autoclave together with 68 g of deionized water and 0.38 g (0.00358 M) of sodium diphosphite, and after thorough purging with N<sub>2</sub>, the temperature was raised to 250 °C over the course of 3 hours with stirring. The reaction was carried out at 250 °C for 1 hour while the autoclave was closed. The stirring was then stopped, and the reaction mixture was withdrawn from the bottom portion of the autoclave under a differential pressure of 10 kg/cm<sup>2</sup>. It was dried overnight in N<sub>2</sub> at 50 °C and 100 mmHg to give a prepolymer. The prepolymer had an  $[\eta]$  (at 30 °C in conc. H<sub>2</sub>SO<sub>4</sub>) of 0.12 dl/g. The prepolymer was further polycondensed in the molten state by a twin-screw extruder (screw diameter 30 mm; L/D=42; barrel temperatures (°C) 80/180/340/340/280/280/260/260; the third, fourth and fifth zones had vents open to the atmosphere; rotating speed 50 rpm; the amount of the prepolymer fed 2 kg/hr;

- 11 -

evacuation by  $N_2$  purging) to give a colorless transparent polymer. The proportion (mole %) of the isophthalic acid component units in the polymer, the proportion (mole %) of the terephthalic acid component units  
5 in the polymer and the MFR (g/10 min.),  $[\eta]$  (at 30 °C in conc.  $H_2SO_4$ ) and glass transition temperature of the polymer are shown in Table 1.

Examples 2-4

The polymers shown in Table 1 were prepared by  
10 the same method as described in Example 1 except that the type or amount of the diamine component was changed.

Example 5

The polymer shown in Table 1 was obtained in the same way as in Example 1 except that 89.22 g (0.537  
15 M) of terephthalic acid, 208.17 g (1.253 M) of isophthalic acid, 106.91 g (0.92 M) of 1,6-diaminohexane, 125.12 g (0.92 M) of m-xylylenediamine, 75 g of deionized water and 0.38 g (0.00358 M) of sodium diphosphite were used as starting materials.

20 Example 6

The polymer indicated in Table 1 was obtained by the same method as described in Example 5 except that all terephthalic acid in Example 5 was replaced by isophthalic acid.

Table 1

	Example 1	Example 2	Example 3	Example 4	Example 5	Example 6
Materials	Acid component (type)	TA/IA	TA/IA	TA/IA	TA/IA	IA
	Amount of the acid component (mole ratio)	30/70	30/70	30/70	30/70	100
	Diamine component (type)	C <sub>6</sub> DA/ACM	C <sub>6</sub> DA/ACM	C <sub>6</sub> DA/DWACM	C <sub>6</sub> DA/AMC	C <sub>6</sub> DA/MD
	Amount of the diamine component (mole ratio)	50/50	75/25	75/25	75/25	50/50
Polymer	Acid component (type)	TA/IA	TA/IA	TA/IA	TA/IA	IA
	Amount of the acid component (mole ratio)	30/70	30/70	30/70	30/70	100
	Diamine component (type)	C <sub>6</sub> DA/ACM	C <sub>6</sub> DA/ACM	C <sub>6</sub> DA/DWACM	C <sub>6</sub> DA/AMC	C <sub>6</sub> DA/MD
	Amount of the diamine component (mole ratio)	49/51	74/26	74/26	75/25	50/50
MFR (g/10 min., 300°C, 2 kg)						
[ $\eta$ ] (dl/g, at 30°C in conc.H <sub>2</sub> SO <sub>4</sub> )						
Glass transition temperature (°C)						
Crystallinity (%)						

Note: The mole ratio of the acid component to the diamine component charged was 1.00:1.03.

Example 7

The polyamide pellets obtained in Example 1 were dried at 100 °C under 1 mmHg for 12 hours, and then hot-pressed at a temperature 120 °C higher than the T<sub>g</sub> of the polymer under a pressure of 100 kg/cm<sup>2</sup> in a nitrogen atmosphere in a press-molding machine, then cold-pressed at a temperature of 20 °C to obtain a transparent press sheet having a thickness of 100 microns. The press sheet was cut to a predetermined size, and dried in an atmosphere of nitrogen at 100 °C under 40 mmHg for 12 hours. The gas-barrier property of the cut press sheet was measured. The results are shown in Table 2.

Examples 8 to 12

In each run, a press sheet was prepared by the same method as in Example 7 except that each of the polymers obtained in Examples 2 to 6 as shown in Table 1 was used. The results are shown in Table 2.

Table 2

	Example 7	Example 8	Example 9	Example 10	Example 11	Example 12
Examples of polyamide production	Example 1	Example 2	Example 3	Example 4	Example 5	Example 6
Gas-barrier property						
Oxygen permeability coefficient (ml·mm/m <sup>2</sup> ·day·atm)	0.7	1.8	1.9	2.1	1.5	1.1
Carbon dioxide permeability coefficient (ml·mm/m <sup>2</sup> ·day·atm)	3.9	6.5	6.9	7.3	3.9	3.2

Example 13

Polyethylene terephthalate (Mitsui PET J125, a product of Mitsui PET Resin Co., Ltd.) was melted by using one extruder. Separately, the polyamide of Example 1 was melted by using another extruder. The molten polymers were respectively fed into a two-kind three-layer pipe die, and a three-layer pipe composed of polyethylene terephthalate/polyamide/polyethylene terephthalate (thickness about 1.2 mm/1.2 mm/1.2 mm). The pipe was cooled with water to obtain a three-layer pipe having an outside diameter of 24.8 mm and a thickness of 3.0 mm. The pipe was then cut and one end was heat-melted to form a bottom portion. The other end was likewise heat-melted to form a faucet portion. Thus, a preform having a total length of 16.5 cm and a weight of 50 g was obtained. Then, by using a biaxial-stretch blow-molding machine (LB01 made by Corpoplast Company), the preform was biaxially stretched at a stretch ratio of 2.5 in the longitudinal direction and 4 in the transverse direction to obtain a multilayered container (polyethylene terephthalate/polyamide/polyethylene terephthalate=about 120 microns/about 120 microns/about 120 microns) having an inner capacity of 1.5 liters. The gas-barrier property of this multilayered container was measured, and the results are shown in Table 3.

Examples 14 to 16

A multilayered container was produced by the method described in Example 13 except that each of the polymers obtained in Examples 2 to 4 as shown in Table 1 was used instead of the polyamide produced in Example 1. The results are shown in Table 3.

Comparative Example 1

A container was produced by the same method as in Example 13 except that only polyethylene terephthalate (Mitsui PET J125, made by Mitsui PET Resin Co., Ltd.) was used. The gas-barrier property of the container was measured.



Comparative Example 2

A polyamide was synthesized by the method described in Example 1 except that 208.17 g (1.253M) of terephthalic acid, 89.22 g (0.537 M) of isophthalic acid  
5 and 213.83 g (1.84M) of 1,6-diaminohexane were used. The resulting polymer was a white crystalline polyamide having a melting point of 310 °C, an  $[\eta]$  of 1.2 dl/g and a crystallinity of 25 %.


A three-layer container was produced by the  
10 same method as in Example 13 using the polyamide and polyethylene terephthalate, and its gas-barrier property was measured.

Table 3


	Example 13	Example 14	Example 15	Example 16	Comparative Example 1	Comparative Example 2
Examples of polyamide production	Example 1	Example 2	Example 3	Example 4	-	-
Gas-barrier property	Oxygen permeability coefficient (ml·mm/m <sup>2</sup> ·day·atm)	1.1	2.7	2.9	3.5	4.6
	Carbon dioxide permeability coefficient (ml·mm/m <sup>2</sup> ·day·atm)	5.9	9.8	11.0	11.7	25.0
						3.8
						12.8

## SCOPE OF CLAIM FOR PATENT

1. An aromatic polyamide characterized in that  
 (1) it is composed of a random arrangement of isophthaloyldiamine component recurring units represented by the following formula (I)



wherein  $\text{R}^{\text{O}}$  is a divalent hydrocarbon group having 4 to 25 carbon atoms, and diacyloyldiamine component recurring units represented by the following formula (II)



wherein  $\text{R}^{\text{O}}$  is as defined above, and Ar is a divalent aromatic hydrocarbon residue containing 6 to 20 carbon atoms other than the 1,3-phenylene group,

- (2) it has such a composition that based on the entire recurring units, the proportion of the isophthaloyldiamine component units is 50 to 100 mole % and the proportion of the diacyloyldiamine component units is 50 to 0 mole %,

(3) it has a melt flow rate (MFR), measured at 300 °C under a load of 2 kg, of 0.01 to 100 g/10 min.,

(4) it has a crystallinity, measured by X-ray diffractometry, of not more than 7 %, and

(5) it has a glass transition temperature ( $T_g$ ) of 110 to 240 °C.

2. The aromatic polyamide set forth in claim 1 wherein the divalent hydrocarbon group having 4 to 25 carbon atoms represented by  $\text{R}^{\text{O}}$  in formulae (I) and (II) is selected from the group consisting of divalent aliphatic hydrocarbon groups having 4 to 25 carbon atoms, divalent alicyclic hydrocarbon groups containing at least



one alicyclic hydrocarbon ring and having 6 to 25 carbon atoms and divalent aromatic hydrocarbon groups containing at least one aromatic hydrocarbon ring and having 6 to 25 carbon atoms.

3. The aromatic polyamide set forth in claim 2 wherein the hydrocarbon group having 4 to 25 carbon atoms for  $R^O$  is a mixture of a divalent aliphatic hydrocarbon group having 4 to 25 carbon atoms and a divalent alicyclic hydrocarbon group containing at least one alicyclic hydrocarbon ring and having 6 to 25 carbon atoms, or a mixture of said divalent aliphatic hydrocarbon and a divalent aromatic hydrocarbon group containing at least one aromatic hydrocarbon ring and having 6 to 25 carbon atoms.

4. The aromatic polyamide set forth in claim 1 wherein the proportion of the isophthaloyldiamine component units of formula (I) is 60 to 90 mole %, and the proportion of the diacyloyldiamine component units of formula (II) is 40 to 10 mole %.

5. The aromatic polyamide set forth in claim 1 which has a melt flow rate of 0.1 to 50 g/min.

6. The aromatic polyamide set forth in claim 1 which has a crystallinity of not more than 5 %.

7. The aromatic polyamide of claim 1 which has a glass transition temperature of 120 to 220 °C.

8. A gas-barrier property imparting agent composed of the aromatic polyamide set forth in any one of claims 1 to 7.

9. Use of the aromatic polyamide set forth in any one of claims 1 to 7 as a gas-barrier imparting agent.

# INTERNATIONAL SEARCH REPORT

00283736

International Application No PCT/JP87/00617

<b>I. CLASSIFICATION OF SUBJECT MATTER</b> (if several classification symbols apply, indicate all) *		
According to International Patent Classification (IPC) or to both National Classification and IPC		
Int.Cl. <sup>4</sup> C08G69/26-69/32, 69/40-69/42		
<b>II. FIELDS SEARCHED</b>		
Minimum Documentation Searched *		
Classification System <sup>1</sup>	Classification Symbols	
IPC	C08G69/26-69/32, 69/40-69/42	
Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in the Fields Searched *		
<b>III. DOCUMENTS CONSIDERED TO BE RELEVANT</b> <sup>14</sup>		
Category *	Citation of Document, <sup>16</sup> with Indication, where appropriate, of the relevant passages <sup>17</sup>	Relevant to Claim No. <sup>18</sup>
Y	JP, B1, 46-41024 (Toray Industries, Inc.) 3 December 1971 (03. 12. 71) Column 2, lines 12 to 37, Drawing (Family: none)	1-9
Y	JP, B1, 49-36959 (DYNAMIT NOBEL AG) 4 October 1974 (04. 10. 74) Column 2, lines 15 to 53 (Family: none)	1, 2, 4-9
Y	JP, A, 53-5250 (Toray Industries, Inc.) 18 January 1978 (18. 01. 78) Column 1, 18th line to 4th line from the bottom (Family: none)	1, 2, 4-9
Y	JP, A, 53-18697 (BAYER AG) 21 February 1978 (21. 02. 78) & DE, A, 2635085 & FR, A, 2360621 & GB, A, 1590528	1-9
<p>* Special categories of cited documents: <sup>19</sup></p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step</p> <p>"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</p> <p>"&amp;" document member of the same patent family</p>		
<b>IV. CERTIFICATION</b>		
Date of the Actual Completion of the International Search <sup>2</sup>	Date of Mailing of this International Search Report <sup>2</sup>	
October 29, 1987 (29. 10. 87)	November 9, 1987 (09. 11. 87)	
International Searching Authority <sup>1</sup>	Signature of Authorized Officer <sup>20</sup>	
Japanese Patent Office		



## FURTHER INFORMATION CONTINUED FROM THE SECOND SHEET

Y	JP, A, 53-64299 (BAYER AG) 8 June 1978 (08. 06. 78) & DE, A, 2652465 & FR, A, 2371474 & GB, A, 1554245 & US, A, 4250297	1, 2, 5-9
Y	JP, A, 53-125497 (BAYER AG) 1 November 1978 (01. 11. 78) & DE, A, 2715413 & FR, A, 2386574 & GB, A, 1590056	1-9
Y	JP, A, 54-71194 (CIBA GEIGY AG) 7 June 1979 (07. 06. 79) & DE, A, 2846514 & FR, A, 2407229 & GB, A, 2008133 & US, A, 4210742	1-9

V. ☐ OBSERVATIONS WHERE CERTAIN CLAIMS WERE FOUND UNSEARCHABLE<sup>11</sup>

This international search report has not been established in respect of certain claims under Article 17(2) (a) for the following reasons:

1. ☐ Claim numbers..... because they relate to subject matter<sup>12</sup> not required to be searched by this Authority, namely:

2. ☐ Claim numbers..... because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out<sup>12</sup>, specifically:

VI. ☐ OBSERVATIONS WHERE UNITY OF INVENTION IS LACKING<sup>11</sup>

This International Searching Authority found multiple inventions in this international application as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims of the international application.

2. ☐ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims of the international application for which fees were paid, specifically claims:

3. ☐ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claim numbers:

4. ☐ As all searchable claims could be searched without effort justifying an additional fee, the International Searching Authority did not invite payment of any additional fee.

## Remark on Protest

☐ The additional search fees were accompanied by applicant's protest.

☐ No protest accompanied the payment of additional search fees.

## FURTHER INFORMATION CONTINUED FROM THE SECOND SHEET

Y	JP, B2, 61-34731 (Teijin Limited) 9 August 1986 (09. 08. 86) Column 3, line 21 to column 4, line 26. (Family: none)	1, 2, 4-9
Y	JP, A, 57-115420 (E I DU PONT DE NEMOURS) 17 July 1982 (17. 07. 82) & EP, A, 53876 & US, A, 4369305	1-9
Y	JP, A, 58-2328 (CIBA GEIGY AG) 7 January 1983 (07. 01. 83) & EP, A, 69067 & US, A, 4429110	1, 2, 4-9

V. ☐ OBSERVATIONS WHERE CERTAIN CLAIMS WERE FOUND UNSEARCHABLE<sup>10</sup>

This International search report has not been established in respect of certain claims under Article 17(2) (a) for the following reasons:

1. ☐ Claim numbers..... because they relate to subject matter<sup>12</sup> not required to be searched by this Authority, namely:

2. ☐ Claim numbers..... because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out<sup>13</sup>, specifically:

VI. ☐ OBSERVATIONS WHERE UNITY OF INVENTION IS LACKING<sup>11</sup>

This International Searching Authority found multiple inventions in this international application as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims of the international application.

2. ☐ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims of the international application for which fees were paid, specifically claims:

3. ☐ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claim numbers:

4. ☐ As all searchable claims could be searched without effort justifying an additional fee, the International Searching Authority did not invite payment of any additional fee.

Remark on Protest

☐ The additional search fees were accompanied by applicant's protest.

☐ No protest accompanied the payment of additional search fees.

**THIS PAGE BLANK (USPTO)**